

Tarmac Trading Limited T3 Ground Floor Trinity Park Bickenhill Lane Solihull Birmingham B37 7ES	25
	0086-CPR-820635
	BS EN 12591 Paving grade bitumen
	160/220
	Dagenham
	1306804-1306921-1306918-1306818/R300/2025

**GENERAL**

PROPERTY	PERFORMANCE	UNITS	METHOD
Penetration at 25 °C	160 - 220	0,1mm	EN 1426
Softening point	35 – 43	°C	EN 1427
Flash Point	≥ 220	°C	EN ISO 2592
Solubility	≥ 99,0	%	EN 12592
Kinematic viscosity at 135 °C	≥ 135	mm <sup>2</sup> /s	EN 12595
<b>Resistance to hardening @163°C</b>			EN 12607-1
Retained penetration	≥ 37	%	
Increase in softening point	≤ 11	°C	
Change of mass	≤ 1,0	%	

Plant code (plant name)	R300 Dagenham
Material code (material description)	1306804 (160/220) 1306921 (160/220 LO) 1306918 (160/220 LT) 1306818 (160/220 LTX)
Date	<b>2025</b>

 Need help? Email us at [ukca@tarmac.com](mailto:ukca@tarmac.com)