

Tarmac Trading Limited T3 Ground Floor Trinity Park Bickenhill Lane Solihull Birmingham B37 7ES	25
	0086-CPR-820635
	BS EN 12591 Paving grade bitumen
	40/60
	Dagenham
	1306776-1306722-1306917/R300/2025

GENERAL

PROPERTY	PERFORMANCE	UNITS	METHOD
Penetration at 25 °C	40 - 60	0,1mm	EN 1426
Softening point	48 - 56	°C	EN 1427
Flash Point	≥230	°C	EN ISO 2592
Solubility	≥ 99,0	%	EN 12592
Kinematic viscosity at 135 °C	≥ 325	mm ² /s	EN 12595
Resistance to hardening @163°C			EN 12607-1
Retained penetration	≥ 50	%	
Increase in softening point	≤ 9	°C	
Change of mass	≤ 0,5	%	

Plant code (plant name)	R300 Dagenham
Material code (material description)	1306776 (40/60) 1306722 (40/60 LO) 1306917 (40/60 LT)
Date	2025
Need help? Email us at ukca@tarmac.com	